

Espuma de PVC 80



Densidad kg/m ³	ASTM D1622	kg/m ³	nominal	80
Resistencia a la compresión	ASTM D1621-10	MPa	average min-ave min-min	1,43 1,22 1,03
Modulo de compresión	ASTM D1621-10	MPa	average min-ave min-min	68 53 44
Resistencia a la rotura	ASTM D1623	MPa	average min-ave min-min	2,60 1,82 1,63
Modulo de rotura	ASTM D1623	MPa	average min-ave min-min	137 107 94
Resistencia al corte	ASTM C273	MPa	average min-ave min-min	1,13 1,06 0,92
Modulo de corte	ASTM C273	MPa	average min-ave min-min	29 25 22
Alargamiento de corte a la rotura	ASTM C273	%	average	20
Medidas estandar		mm		1020 2180 72